


We claim:

1. A biomedical device formed from the polymerization product of a monomeric mixture comprising a poly(2-oxazoline) endcapped with an ethylenically unsaturated radical.

2. The device of claim 1, which is an ophthalmic lens.

3. The lens of claim 2, wherein the poly(2-oxazoline) is a macromonomer of the formula:




where R is a polymerizable, ethylenically unsaturated radical;

R' is selected from the group consisting of alkyl, haloalkyl, alkene, alkyne, cycloalkyl, halocycloalkyl, aryl, haloaryl, aralkyl and haloaralkyl; and

n is at least 2.

4. The lens of claim 3, wherein R is



wherein:

R<sub>23</sub> is hydrogen or methyl;

each R<sub>24</sub> is hydrogen, an alkyl radical having 1 to 6 carbon atoms, or a -CO-Y-R<sub>26</sub> radical wherein Y is -O-, -S- or -NH-;

R<sub>25</sub> is a single bond or a divalent alkylene radical having 1 to 10 carbon atoms;

R<sub>26</sub> is an alkyl radical having 1 to 12 carbon atoms;

X denotes -CO- or -OCO-;


Q denotes -O- or -NH-;

Ar denotes an aromatic radical having 6 to 30 carbon atoms; b is 0 to 6; c is 0 or 1; d is 0 or 1; and e is 0 or 1.

5. The lens of claim 4, wherein R is selected from the group consisting of (meth)acrylate, (meth)acrylamide, allyl and styrene radicals.

6. The lens of claim 3, wherein R' is selected from the group consisting of C<sub>1</sub>-C<sub>6</sub> alkyl and phenyl.

7. The lens of claim 2, wherein the poly(2-oxazoline) is a telechelic of the formula:




where each R is independently a polymerizable, ethylenically unsaturated radical;

each R' is independently selected from the group consisting of alkyl, haloalkyl, alkene, alkyne, cycloalkyl, halocycloalkyl, aryl, haloaryl, aralkyl and haloaralkyl;

Z is a divalent linkage; and

each of x and y is at least 1.

8. The lens of claim 7, wherein R is



wherein:

R<sub>23</sub> is hydrogen or methyl;

each R<sub>24</sub> is hydrogen, an alkyl radical having 1 to 6 carbon atoms, or a -CO-Y-R<sub>26</sub> radical wherein Y is -O-, -S- or -NH-;

R<sub>25</sub> is a single bond or a divalent alkylene radical having 1 to 10 carbon atoms;

R<sub>26</sub> is an alkyl radical having 1 to 12 carbon atoms;

X denotes -CO- or -OCO-;

Q denotes -O- or -NH-;

Ar denotes an aromatic radical having 6 to 30 carbon atoms; b is 0 to 6; c is 0 or 1; d is 0 or 1; and e is 0 or 1.

9. The lens of claim 8, wherein R is selected from the group consisting of (meth)acrylate, (meth)acrylamide, allyl and styrene radicals.

10. The lens of claim 7, wherein R' is selected from the group consisting of C<sub>1</sub>-C<sub>6</sub> alkyl and phenyl.

11. The lens of claim 7, wherein Z is selected from the group consisting of a single bond and C<sub>1</sub>-C<sub>6</sub> alkylene optionally including ether linkages.

12. The lens of claim 2, wherein the monomeric mixture further comprises at least one hydrophilic monomer selected from the group consisting of ethylenically unsaturated carboxylic acids, (meth)acrylic substituted alcohols, vinyl lactams, and (meth)acrylamides.

13. The lens of claim 12, wherein the monomeric mixture comprises at least one hydrophilic monomer selected from the group consisting of (meth)acrylic acid, 2-hydroxyethyl(meth)acrylate, glyceryl(meth)acrylate, N-vinyl pyrrolidone, methacrylamide and N,N-dimethylacrylamide.

14. The lens of claim 2, wherein the monomeric mixture further comprises at least one silicone-containing monomer.

15. The lens of claim 14, wherein the monomeric mixture comprises at least one silicone-containing monomer selected from the group consisting of methacryloxypropyl

tris(trimethylsiloxy)silane, pentamethyldisiloxanyl methylmethacrylate, tris(trimethylsiloxy) methacryloxy propylsilane, phenyltetramethyl-disiloxanylethyl acrylate, methyldi(trimethylsiloxy)methacryloxymethyl silane, 3-[tris(trimethylsiloxy)silyl] propyl vinyl carbamate, 3-[tris(trimethylsiloxy)silyl] propyl allyl carbamate, and 3-[tris(trimethylsiloxy)silyl] propyl vinyl carbonate.

16. The lens of claim 2, which is a contact lens.
17. The lens of claim 2, which a hydrogel contact lens.
18. The lens of claim 2, which is an intraocular lens.
19. The lens of claim 18, which is a hydrogel intraocular lens.